## **Product Information**

## JB GERMAN OIL Scooter Young Power 4T 10W-40

J2066



## Description

JB GERMAN OIL Scooter Young Power 4T 10W-40 is a engine oil for demanding 4-stroke motorbikes. It allows for fuel-saving engine operation and is specifically designed for wet and lubricated couplings. JB GERMAN OIL Scooter Young Power 4T 10W-40 is characterized by its excellent cold starting properties, as it ensures optimum lubrication reliability during the cold-running phase.

## Instructions for use

JB GERMAN OIL Scooter Young Power 4T 10W-40 is especially suitable as a high-performance, smooth-running engine oil for all motorcycles, when the specification JASO MA2 T904:2006 SAE 10W-40 is required. JB GERMAN OIL Scooter Young Power 4T 10W-40 meets the high-tech demands of the latest high-performance engine generation. For professional racing we recommend our racing products.

Quality classification	
Specification	
• API SL	• JASO MA2
Recommendation	
• Aprilia	• Moto-Guzzi
• BMW	• Suzuki
• Ducati	• Triumph
• Honda	• Yamaha
• Kawasaki	
Properties	
<ul> <li>Excellent cold starting properties</li> </ul>	Very stable viscosity index
<ul> <li>Very good detergent and dispersing properties</li> </ul>	Fast lubrication of the engine
<ul> <li>Low evaporation, thus low oil consumption</li> </ul>	<ul> <li>No oil-related deposits in combustion chambers, in piston ring zones and valves</li> </ul>

- Low evaporation, thus low oil consumption
- Prevention of silting, varnish, coking and corrosion

Technical specifications				
Properties	Data	Unit	Testing under	
Kinematic Viscosity at 40°C	97,7	mm²/s	DIN 51659-2:2017-02	
Kinematic Viscosity at 100°C	14,4	mm²/s	DIN 51659-2:2017-02	
Viscosity Index	152		DIN ISO 2909:2004-08	
Appearance	YELLOWBROWN		VISUELL	
Viscosity CCS at -25°C	6400	mPa*s	ASTM D 5293:2020	
Density at 15°C	864	kg/m³	DIN EN ISO 12185:1997-11	
Pour Point	-36	°C	ASTM D 7346:2015	
Total Base Number (TBN)	7,7	mgKOH/g	ASTM D 2896:2015	

JB German Oil GmbH | Wölzower Weg 13 - 19 | D-19243 Wittenburg | Telefon: +49 (0) 38852 90620 | Telefax: +49 (0) 38852 906220

Notice: To the best of our knowledge, all of the information provided was in accordance with the latest findings and developments. Our products are subject to continuous development. For this reason, our products, the manufacturing processes and all related information on this product page are subject to change at any time and without notice, unless customer-specific agreements exist. The data listed are based on standardized test procedures under appropriate laboratory conditions and are to be regarded as general, non-binding reference values.