Product Information

JB GERMAN OIL Longlife P5 SAE 5W-40

J2085



Description

JB GERMAN OIL Longlife P5 SAE 5W-40 is a synthetic smooth-running engine oil for petrol and diesel car engines with or without turbocharging and direct injection. It is characterized by its excellent cold starting properties, minimization of fuel consumption, friction and wear. Extended oil change intervals as per manufacturer's instructions. JB GERMAN OIL Longlife P5 SAE 5W-40 offers maximum operational safety in all driving conditions, for example in extreme stop-and-go traffic in big cities, as well as during high-speed motorway driving.

Instructions for use

JB GERMAN OIL Longlife P5 SAE 5W-40 is an energy-efficient engine oil for year-round use, and is ideal for modern petrol and diesel car engines.

| Quality classification | |
|--------------------------------------|-------------------------|
| Specification | |
| • API SP | • ACEA A3/B4 |
| Recommendation | |
| BMW Longlife-01 | • Porsche A40 |
| Chrysler MS-10725, Chrysler MS-12991 | • PSA B71 2296 |
| • Fiat 9.55535-H2/-M2 | • Renault RN0700/RN0710 |
| • MB 226.5, MB 229.3 | • VW 502 00/505 00 |

Properties

• Opel GM LL-B-025

- Fuel savings under all operating conditions
- Neutrality towards sealants
- Low evaporation, thus low oil consumption
- Extended oil change intervals protect natural resources
- Excellent cold starting properties, even at low temperatures
- Very good detergent and dispersing properties
- Extensive protection against wear, corrosion and foaming

| Technical specifications | | | |
|------------------------------|-------------|---------|--------------------------|
| Properties | Data | Unit | Testing under |
| Kinematic Viscosity at 40°C | 78,1 | mm²/s | DIN 51659-2:2017-02 |
| Kinematic Viscosity at 100°C | 13,3 | mm²/s | DIN 51659-2:2017-02 |
| Viscosity Index | 174 | | DIN ISO 2909:2004-08 |
| Appearance | YELLOWBROWN | | VISUELL |
| Viscosity CCS at -30°C | 5530 | mPa*s | ASTM D 5293:2020 |
| Density at 15°C | 850 | kg/m³ | DIN EN ISO 12185:1997-11 |
| Pour Point | -39 | °C | ASTM D 7346:2015 |
| Total Base Number (TBN) | 11,5 | mgKOH/g | ASTM D 2896:2015 |