Product Information

JB GERMAN OIL Mineral Super 10W

J2023

Description

JB GERMAN OIL Mineral Super 10W is a universally applicable, high-performance, mono-grade engine oil for use in diesel lorry engines with and without turbo charging, as well as for stationary systems. JB GERMAN OIL Mineral Super 10W offers a balanced additive package and guarantees high wear and corrosion protection.

Instructions for use

JB GERMAN OIL Mineral Super 10W is used in diesel lorry engines with and without turbo charging, as well as in stationary systems. The operating instructions of the automobile and engine manufacturer must be observed.

Quality classification

Specification

- API SF/CD
- CCMC G4
- MIL-L-2104 D
- MIL-L-46152 B

Recommendation

- MB 227.0, MB 228.0, DTFR 13D100 (235.27)
- Voith Retarder A

Properties

- A very stable and excellent
- High oxidation stability
- Good lubrication properties, even at high oil temperatures
- Prevention of wear
- Neutrality towards sealants
- Prevents black sludge
- Viscosity and temperature behavior
- Good shear stability
- Ideal for difficult operating conditions
- Compelling detergent/dispersant properties
- Good cold starting properties

Technical specifications

Properties	Data	Unit	Testing under
Kinematic Viscosity at 40°C	43,2	mm²/s	DIN 51659-2:2017-02
Kinematic Viscosity at 100°C	7,0	mm²/s	DIN 51659-2:2017-02
Viscosity Index	120		DIN ISO 2909:2004-08
Appearance	BROWN		VISUELL
Density at 15°C	866	kg/m³	DIN EN ISO 12185:1997-11
Pour Point	-30	°C	ASTM D 7346:2015

JB German Oil GmbH | Wölzower Weg 13 - 19 | D-19243 Wittenburg | Telefon: +49 (0) 38852 90620 | Telefax: +49 (0) 38852 906220

Notice: To the best of our knowledge, all of the information provided was in accordance with the latest findings and developments. Our products are subject to continuous development. For this reason, our products, the manufacturing processes and all related information on this product page are subject to change at any time and without notice, unless customer-specific agreements exist. The data listed are based on standardized test procedures under appropriate laboratory conditions and are to be regarded as general, non-binding reference values.