Product Information

JB GERMAN OIL F1 Racing Extrem SAE 10W-60

J2076

Description

JB GERMAN OIL F1 Racing Extrem SAE 10W-60 is a synthetic, multi-grade engine oil with specially selected base oils. A very high proportion of Group IV PAO makes it a very special engine oil, which can also satisfy the highest requirements. Thanks to its special additives, JB GERMAN OIL F1 Racing Extrem SAE 10W-60 is also suitable for extreme racing. JB GERMAN OIL F1 Racing Extrem SAE 10W-60 is ideally suited to modern petrol engines under the heaviest of loads during car racing. JB GERMAN OIL F1 Racing Extrem SAE 10W-60 ensures an optimal lubrication layer, even at very high operating temperatures.

Instructions for use

JB GERMAN OIL F1 Racing Extrem SAE 10W-60 was specially developed for speedway car racing and may therefore also be used in the harshest operating conditions. Its particularly modern and high-quality basic ingredients, in combination with a very specially selected additive package, prevent deposits on engine parts that are subject to high stress.

Quality classification

Specification

- API SP/CF
- ACEA A3/B4

Recommendation

- BMW M Serie
- Fiat 9.55535-H3
- MB 229.1
- VW 501 01/505 00

Properties

- A highly-modern, synthetic engine oil for use in extreme racing
- High oil film stability to prevent wear
- Low evaporation, thus low oil consumption
- Suitable for catalytic converters
- Extended oil change intervals protect natural resources
- A very stable and excellent viscosity behavior and shear stability
- Continuous high oil pressure
- Highest possible protection against wear, corrosion and foaming
- Black sludge is prevented from forming

Technical specifications

Properties	Data	Unit	Testing under
Kinematic Viscosity at 40°C	159,0	mm²/s	DIN 51659-2:2017-02
Kinematic Viscosity at 100°C	23,3	mm²/s	DIN 51659-2:2017-02
Viscosity Index	176		DIN ISO 2909:2004-08
Appearance	YELLOWBROWN		VISUELL
Density at 15°C	848	kg/m³	DIN EN ISO 12185:1997-11
Pour Point	-54	°C	ASTM D 7346:2015

JB German Oil GmbH | Wölzower Weg 13 - 19 | D-19243 Wittenburg | Telefon: +49 (0) 38852 90620 | Telefax: +49 (0) 38852 906220

Notice: To the best of our knowledge, all of the information provided was in accordance with the latest findings and developments. Our products are subject to continuous development. For this reason, our products, the manufacturing processes and all related information on this product page are subject to change at any time and without notice, unless customer-specific agreements exist. The data listed are based on standardized test procedures under appropriate laboratory conditions and are to be regarded as general, non-binding reference values.